



Lilly-Ram Chemical Company, LLC  
 1740 E. Monticello Ct.  
 Ontario, CA 91761

Ram's Gelcoat technology significantly reduces styrene emissions, shrinkage, and costly overspray.

In addition to lower emissions and shrinkage, Ram gelcoat yields improved weatherability and osmotic blister resistance when compared to similar conventional gelcoats.

**Advantages:**

- 50% Less Styrene Emissions
- 30-60% Less Shrinkage
- Reduced Overspray
- Ease of Application
- Enhanced Weather ability
- Crack resistance
- Osmotic Blister Resistance
- Long term durability
- UV light stability

**UNCURED GELCOAT PROPERTIES**  
 (All properties based on 2.0% MEKP)

- Gel time @ 77°F .....10-12 min.
- Gel to peak.....8 - 10 min.
- Film cure @ 77°F .....45 max.
  
- Visc. @ 77°F  
 (LVF #4 @ 60rpm-cps).....3000 - 3500
- Thix index (6/60).....5.0 -6.25
- Sag resistance.....20 - 25 mils
  
- Hegman grind .....4 minimum
- Weight per gallon.....10.0 – 12.0 lbs
- Stability @ 77°F  
 Closed Container.....2 months
- Hide @ 15 mils (wet).....complete

**CURED GELCOAT PROPERTIES**

- Y Flex elongation  
 ASTM D790.....1.5 – 1.7%
- Y HDT ASTM D648.....175 - 190°F

**TYPICAL APPLICATIONS** Marine, sanitary ware, wind blades recreational vehicles, and other open mold hand lay-up applications.

**COLORS**

A range of colors as well as custom colors are available on short notice. Using computer spectrophotometry, Ram can match your color sample.

Ram gelcoats are intended for use under controlled industrial conditions and are not recommended to be used below 70°F.

The information contained in this data sheet has been developed through the application of accepted laboratory practice and is believed to be reliable. Since the conditions of application and use of our products are beyond our control, no warranty or representation is expressed or implied regarding accuracy of the information, the results to be obtained from the use of the product, or that such use will not infringe on any patent. The information is furnished with the express conditions that the user will evaluate it through testing and determine the suitability of the product. Lilly-Ram Chemical Company, LLC will not be liable for any injury or damage arising from the application of this information. Lilly-Ram disclaims any warranty or merchantability of warranty of fitness for a particular use.